

CLAIMS

1. A method for improving the antimicrobial activity of a polymer derived from acrolein monomer wherein the polymer has been oxidized in air to form an oxidised acrolein polymer comprising carboxyl groups, said method comprising:
- 5 providing a solution of the oxidized acrolein polymer comprising carboxyl groups in a mixture containing water and a hydroxylic solvent including an alcohol selected from the group consisting of polyols, polyethylene glycols and alkanols; and
- 10 heating the solution at a temperature in the range of from 40 to 150°C for a period sufficient to improve the antimicrobial activity of the acrolein polymer.
- 15 2. A method according to claim 1 wherein said oxidised polymer comprising carboxyl groups is formed by a method of heating a solid acrolein polymer in air at an elevated temperature to form carboxyl groups.
- 20 3. A method according to claim 2 wherein said acrolein polymer comprising carboxyl groups has been formed by heating in air at a temperature between 80°C and 100°C.
- 25 4. A method according to claim 2 wherein the acrolein polymer comprising carboxyl groups has been formed by heating in air at a temperature of about 85°C.
5. A method according to claim 1 wherein the pH of the solvent is in the range of from 7 to 9.
- 30 6. A method according to claim 1 wherein the pH of the solvent is about 8.
7. A method according to claim 2 or claim 3 wherein the solvent includes an alkali selected from an alkali hydroxide, alkali carbonate and mixtures thereof.

35

8. A method according to claim 2 or claim 3 wherein the alkali is sodium hydroxide, sodium carbonate or mixture thereof.

9. A method according to claim 1, characterised in that the solution is heated in the range of 40 to 115°C.

10. A method according to claim 1, characterised in that the solution is heated in the range of 70-115°C.

11. A method according to claim 9 wherein the solution is heated to about 100°C.

12. A method according to any one of claims 1 to 3, characterised in that the solution is heated for a period of between 1 to 1,400 hours, thereby increasing antimicrobial activity of the polymers.

13. A method according to any one of the preceding claims, characterised in that the solution is heated for a period in the range of from 4 to 60 hours.

14. A method according to claim 11, characterized in that the hydroxylic solvent is polyethylene glycol and is present in the solution in an amount of between 50 and 99% by weight of the solution.

15. A method according to claim 14, characterized in that polyethylene glycol is present in the solution in an amount of between 64 and 95% by weight of the solution.

16. A method according to any one of the preceding claims, characterized by the addition of base or alkali to the polymers before and/or during heating, thereby enhancing the antimicrobial activity of the polymers.

17. A method according to any one of the preceding claims, characterised in that the release of free acrolein monomer by the acrolein polymer is reduced.

21

18. An antimicrobial compound or composition prepared by the method of any one of the preceding claims.
19. A preservative disinfectant or antiseptic or composition prepared wholly or in part by the method of any one of claims 1 to 16.

5

Sub
a3

10009139 110801